Room 202, 2nd Floor, No.12th Building of Xinhe Tongfuyu Industrial Park, Fuhai Street, Baoan District,

Shenzhen, Guangdong, China

Tel: (86)755-85277785 Fax: (86)755-23705230

Http://www.aoc-cert.com Email: postmaster@aoc-cert.com

File administrators

Report No.:AOC250527012R

TEST REPORT

Client company	:	Dongguan Excel Jointure Acrylic Products LTD	
Client address	:	Shang Keng Industrial District, Chang Ping Town I Province, PRC	Dongguan Guangdong
Manufacturer	:	Dongguan Excel Jointure Acrylic Products LTD	
Address	:	Shang Keng Industrial District, Chang Ping Town I Province, PRC	Dongguan Guangdong
Report on the submitted	san	ples said to be:	
Sample Name	:	Promotion materials, Universal Materials, Indoor mate machine holder	rial, SI 4.1, Single
Trade Mark	:	Honor	
Style/ Item No.	:	9711AFDE, 9711AFDF	
Sample Receiving Date	:	May 20, 2025	
Testing Period	:	May 20, 2025 ~ May 27, 2025	
Results	:	Please refer to next page(s).	
********	*****	***********************	*********
Summary of Test Result	S:		
TEST REQUEST			CONCLUSION
A RoHS Directive (EU) 201	7/2102 amending Annex II to Directive 2011/65/EU.	POSITIVE
Signed for and on behalf of	·**** of AC	**************************************	**********
orginal for and on bonding	(A1
Written By:		Juny Su Approved by:	Alice zhou
		Sunny Su	Alice Zhou

Manager

Room 202, 2nd Floor, No.12th Building of Xinhe Tongfuyu Industrial Park, Fuhai Street, Baoan District,

Shenzhen, Guangdong, China

Tel: (86)755-85277785 Fax: (86)755-23705230

Http://www.aoc-cert.com Email: postmaster@aoc-cert.com

Report No.:AOC250527012R

Results:

A. EU RoHS Directive 2011/65/EU and its amendment directives on XRF

Test method: With reference to IEC 62321-3-1:2013, Screening by X-ray Fluorescence Spectroscopy (XRF)

Seq.			ı	Results	5	
No.	5.	Pb	Cd	Hg	Cr	Br
1	White plasitc enclosure	BL	BL	BL	BL	BL
2	White wire	BL	BL	BL	BL	BL
3	Silver metal interface	BL	BL	BL	BL	BL
4	Silver metal type-C interface	BL	BL	BL	BL	BL
5	Silver metal screw	BL	BL	BL	BL	BL
6	Connector	BL	BL	BL	BL	BL
7	Chips of resistance	BL	BL	BL	BL	BL
8	Chips of capacitance	BL	BL	BL	BL	BL
9	PCB	BL	BL	BL	BL	BL
10	Solder on PCB	BL	BL	BL	BL	BL

Room 202, 2nd Floor, No.12th Building of Xinhe Tongfuyu Industrial Park, Fuhai Street, Baoan District,

Shenzhen, Guangdong, China

Tel: (86)755-85277785 Fax: (86)755-23705230

Http://www.aoc-cert.com Email: postmaster@aoc-cert.com

Report No.:AOC250527012R

Note:

-- = Not Conducted

* = Screening by XRF and detected by chemical method. The test results of chemical method please refer to next pages.

Results were obtained by XRF for primary screening, and further chemical testing by ICP (for Cd, Pb, Hg), UV-Vis (for Cr(VI)) and GC-MS (for PBBs, PBDEs) are recommended to be performed, if the concentration exceeds the below warning value according to IEC 62321-3-1:2013.

Element	Unit	Non-metal	Metal	Composite Material
Cd	mg/kg	BL≤70-3σ <x <130+3σ≤OL</x 	BL≤70-3σ <x <130+3σ≤OL</x 	BL≤50-3σ <x <150+3σ≤OL</x
Pb	mg/kg	BL≤700-3σ <x <1300+3σ≤OL</x 	BL≤700-3σ <x <1300+3σ≤OL</x 	BL≤500-3σ <x <1500+3σ≤OL</x
Hg	mg/kg	BL≤700-3σ <x <1300+3σ≤OL</x 	BL≤700-3σ <x <1300+3σ≤OL</x 	BL≤500-3σ <x <1500+3σ≤OL</x
Cr	mg/kg	BL≤700-3σ <x< td=""><td>BL≤700-3σ<x< td=""><td>BL≤500-3σ<x< td=""></x<></td></x<></td></x<>	BL≤700-3σ <x< td=""><td>BL≤500-3σ<x< td=""></x<></td></x<>	BL≤500-3σ <x< td=""></x<>
Br	mg/kg	BL≤300-3σ <x< td=""><td></td><td>BL≤250-3σ<x< td=""></x<></td></x<>		BL≤250-3σ <x< td=""></x<>

Room 202, 2nd Floor, No.12th Building of Xinhe Tongfuyu Industrial Park, Fuhai Street, Baoan District,

Shenzhen, Guangdong, China

Tel: (86)755-85277785 Fax: (86)755-23705230

Http://www.aoc-cert.com Email: postmaster@aoc-cert.com

Report No.:AOC250527012R

Note:

BL = Below Limit
OL = Over Limit
X = Inconclusive

The XRF screening test for RoHS elements – The reading may be different to the actual content in the sample be of non-uniformity composition.

iii The maximum permissible limit is quoted from the document 2005/618/EC amending RoHS directive 2011/65/EU:

RoHS Restricted Substances	Maximum Concentration Value (mg/kg) (by weight in homogenous materials)
Cadmium (Cd)	100
Lead (Pb)	1000
Mercury (Hg)	1000
Hexavalent Chromium (Cr(VI))	1000
Polybrominated biphenyls (PBBs)	1000
Polybrominated diphenylethers (PBDEs)	1000
Bis(2-ethylhexyl) phthalate(DEHP)	1000
Butyl benzyl phthalate(BBP)	1000
Dibutyl phthalate(DBP)	1000
Diisobutyl phthalate(DIBP)	1000

Disclaimers:

This XRF Screening report is for reference purposes only. The applicant shall make its/his/her own judgment as to whether the information provided in this XRF screening report is sufficient for its/his/her purposes.

The result shown in this XRF screening report will differ based on various factors, including but not limited to, the sample size, thickness, area, surface flatness, equipment parameters and matrix effect (e.g. plastic, rubber, metal, glass, ceramic etc.). Further wet chemical pre-treatment with relevant chemical equipment analysis are required to obtain quantitative data.

Room 202, 2nd Floor, No.12th Building of Xinhe Tongfuyu Industrial Park, Fuhai Street, Baoan District,

Shenzhen, Guangdong, China

Tel: (86)755-85277785 Fax: (86)755-23705230

Http://www.aoc-cert.com Email: postmaster@aoc-cert.com

Report No.:AOC250527012R

B. The Test Results of Chemical Method:

Test method:

Lead & Cadmium Content:

With reference to IEC 62321-5:2013, by acid digestion and analysis was performed by inductively coupled plasma atomic emission spectrometer (ICP-AES)

Mercury Content:

With reference to IEC 62321-4:2013, by acid digestion and analysis was performed by inductively coupled plasma atomic emission spectrometer (ICP-AES)

Hexavalent Chromium Content:

With reference to IEC 62321-7-1:2013, by alkaline digestion and analysis was performed by UV-visible spectrophotometer (UV-Vis)

PBBs & PBDEs Content:

With reference to IEC 62321-6:2015, by solvent extraction and analysis was performed by gas chromatographic-mass spectrometer (GC-MS)

Phthalates Content:

With reference to IEC 62321-8:2017, by gas chromatography-mass spectrometry (GC-MS)

1) The test results of Lead (Pb)

Itam	l lni4	MDI	Res	ults	Limit	
Item	Unit	MDL	(1)	(2)	Limit	
Lead Content (Pb)	mg/kg	2	38	21	1000 mg/kg	
Conclusion	1	1	Pass	Pass	/	

Shenzhen AOCE Electronic Technology Service Co., Ltd. Room 202, 2nd Floor, No.12th Building of Xinhe Tongfuyu Industrial Park, Fuhai Street, Baoan District,

Shenzhen, Guangdong, China

Tel: (86)755-85277785 Fax: (86)755-23705230

Email: postmaster@aoc-cert.com Http://www.aoc-cert.com

Report No.:AOC250527012R

2) The test results of PBBs & PBDEs

lta-m	I I I I I I I	MDI	Res	I imais	
Item	Unit	MDL	1	2	Limit
Polybrominated Biphenyls (PBBs)					
Monobromobiphenyl	mg/kg	5	N.D.	N.D.	
Dibromobiphenyl	mg/kg	5	N.D.	N.D.	
Tribromobiphenyl	mg/kg	5	N.D.	N.D.	
Tetrabromobiphenyl	mg/kg	5	N.D.	N.D.	
Pentabromobiphenyl	mg/kg	5	N.D.	N.D.	
Hexabromobiphenyl	mg/kg	5	N.D.	N.D.	
Heptabromobiphenyl	mg/kg	5	N.D.	N.D.	
Octabromobiphenyl	mg/kg	5	N.D.	N.D.	
Nonabromodiphenyl	mg/kg	5	N.D.	N.D.	
Decabromodiphenyl	mg/kg	5	N.D.	N.D.	
Total content	mg/kg	1	N.D.	N.D.	1000 mg/kg
Polybrominated Diphenylethers (PBDEs)(Mon-Deca)					
Monobromodiphenyl ether	mg/kg	5	N.D.	N.D.	
Dibromodiphenyl ether	mg/kg	5	N.D.	N.D.	
Tribromodiphenyl ether	mg/kg	5	N.D.	N.D.	
Tetrabromodiphenyl ether	mg/kg	5	N.D.	N.D.	
Pentabromodiphenyl ether	mg/kg	5	N.D.	N.D.	
Hexabromodiphenyl ether	mg/kg	5	N.D.	N.D.	
Heptabromodiphenyl ether	mg/kg	5	N.D.	N.D.	
Octabromodiphenyl ether	mg/kg	5	N.D.	N.D.	
Nonabromodiphenyl ether	mg/kg	5	N.D.	N.D.	
Decabromodiphenyl ether	mg/kg	5	N.D.	N.D.	
Total content	mg/kg	1	N.D.	N.D.	1000 mg/kg

Room 202, 2nd Floor, No.12th Building of Xinhe Tongfuyu Industrial Park, Fuhai Street, Baoan District,

Shenzhen, Guangdong, China

Tel: (86)755-85277785 Fax: (86)755-23705230

Http://www.aoc-cert.com Email: postmaster@aoc-cert.com

Report No.:AOC250527012R

Itam	Unit	Unit MDL			Results		Limit	
Item	Unit	MIDL	(1)	(2)	(3)	(4)	(5)	Limit
Dibuyl Phthalate(DBP)	mg/kg	50	N.D.	N.D.	N.D.	N.D.	N.D.	1000 mg/kg
Benzylbutyl Phthalate(BBP)	mg/kg	50	N.D.	N.D.	N.D.	N.D.	N.D.	1000 mg/kg
Bis(2-ethylhexyl) Phthalate(DEHP)	mg/kg	50	N.D.	N.D.	N.D.	N.D.	N.D.	1000 mg/kg
Diispbutyl phthalate(DIBP)	mg/kg	50	N.D.	N.D.	N.D.	N.D.	N.D.	1000 mg/kg

Item	Unit	MDL		Results				Limit	
item	Unit	MIDL	(6)	(7)	(8)	(9)	(10)	LIIIII	
Dibuyl Phthalate(DBP)	mg/kg	50	N.D.	N.D.	N.D.	N.D.	N.D.	1000 mg/kg	
Benzylbutyl Phthalate(BBP)	mg/kg	50	N.D.	N.D.	N.D.	N.D.	N.D.	1000 mg/kg	
Bis(2-ethylhexyl) Phthalate(DEHP)	mg/kg	50	N.D.	N.D.	N.D.	N.D.	N.D.	1000 mg/kg	
Diispbutyl phthalate(DIBP)	mg/kg	50	N.D.	N.D.	N.D.	N.D.	N.D.	1000 mg/kg	

Item	Unit	MDL		Results		Limit	
item	Unit		(11)	 			Limit
Dibuyl Phthalate(DBP)	mg/kg	50	N.D.	 			1000 mg/kg
Benzylbutyl Phthalate(BBP)	mg/kg	50	N.D.	 			1000 mg/kg
Bis(2-ethylhexyl)	mg/kg	50	N.D.	 			1000 mg/kg
Phthalate(DEHP)	ilig/kg	30	IN.D.				1000 mg/kg
Diispbutyl phthalate(DIBP)	mg/kg	50	N.D.	 			1000 mg/kg

Note:

- N.D. = Not Detected or less than MDL
- mg/kg = ppm
- MDL = Method Detection Limit
- Photo appendix is included.

Room 202, 2nd Floor, No.12th Building of Xinhe Tongfuyu Industrial Park, Fuhai Street, Baoan District,

Shenzhen, Guangdong, China

Tel: (86)755-85277785 Fax: (86)755-23705230

Http://www.aoc-cert.com Email: postmaster@aoc-cert.com

Report No.:AOC250527012R

Appendix

Photograph of Sample



Fig.1




Fig.2

Room 202, 2nd Floor, No.12th Building of Xinhe Tongfuyu Industrial Park, Fuhai Street, Baoan District,

Shenzhen, Guangdong, China

Tel: (86)755-85277785 Fax: (86)755-23705230

Http://www.aoc-cert.com Email: postmaster@aoc-cert.com

Report No.:AOC250527012R



Fig.3



Fig.4

AOCE authenticate the photo on original report only

****** End of Report ********